

EP 0007207 (1)
F01D5/28- G05D5/02-
B05B13/04-48B21F-G01D5/30-

-6- BASIC DOC. -

location number:

0 007 207

A1

Office européen des brevets

EUROPEAN PATENT APPLICATION

(21) Application number: 79301288.1

(22) Date of filing: 03.07.79

(51) Int. Cl.³: B 05 B 13/04
B 05 B 12/00, C 23 C 7/00
F 01 D 5/28, G 05 D 5/02
G 01 D 5/30

(30) Priority: 11.07.78 US 923693

(43) Date of publication of application:
23.01.80 Bulletin 80/2

(84) Designated Contracting States:
BE CH DE FR GB NL SE

(71) Applicant: TRW INC.
One Space Park
Redondo Beach California 90278(US)

(72) Inventor: Derkacs, Thomas
6786 Seneca Drive
Mayfield, Ohio 44143(US)

(72) Inventor: Fetheroff, Charles Walter
30612 Ronald Drive
Willowick, Ohio 44094(US)

(72) Inventor: Matay, Istvan Mihaly
8943 State Road
North Royalton, Ohio 44133(US)

(72) Inventor: Toth, Istvan Jozsef
25869 Euclid-Chagrin Parkway
Richmond Heights, Ohio 44143(US)

(74) Representative: Abbie, Andrew Kenneth et al,
A.A. Thornton & Co 303-306 High Holborn
London WC1V 7LE(GB)

(54) Method and apparatus for applying a covering of material to a workpiece; airfoil having a covering, and method and apparatus for determining the location of a surface.

(57) Although the method and apparatus of the present invention can be utilized to apply either a uniform or a non-uniform covering of material over many different workpieces, the apparatus (20) is advantageously utilized to apply a thermal barrier covering (64) to an airfoil (22) which is used in a turbine engine. The airfoil is held by a gripper assembly (86) while a spray gun (24) is effective to apply the covering over the airfoil. When a portion of the covering has been applied, a sensor (28) is utilized to detect the thickness of the covering. A control apparatus (32) compares the thickness of the covering of material which has been applied with the desired thickness and is subsequently effective to regulate the operation of the spray gun to adaptively apply a covering of a desired thickness with an accuracy of at least plus or minus 0.0015 inches (1.5 mils) despite unanticipated process variations.




FIG. 1

DOC

EP 0 007 207 A1

- 1 -

TITLE MODIFIED
see front pageMethod and apparatus for use in making an object.Background of the Invention

The present invention relates to a new and improved method and apparatus for making an object. The method and apparatus can advantageously be utilized to effect the accurate application of a covering having either a uniform or non-uniform thickness to a workpiece, that is to any base material capable of receiving the covering.

There are many known prior art devices for applying a covering to a workpiece. Thus, U.S. Patent No. 3,953,704 discloses the concept of applying a covering of metal to a workpiece which is a ceramic substrate. The metal covering is applied by a plasma spray gun and the workpiece can be positioned along any one of three axes by a drive apparatus. Although this patent contemplates that the workpiece will be moved along three axes, the patent does not contemplate that the workpiece will be rotated about any of the axes to vary the angular orientation of the workpiece relative to the plasma spray gun.

The concept of rotating a welding nozzle about an axis to apply a bead to the inside of a workpiece which is a pump casing, is disclosed in U.S. Patent No. 3,627, 973. The apparatus disclosed in this patent is utilized

- 2 -

to repair the inside of the pump casing by depositing a plurality of beads of material along the inside of the casing. The welding nozzle is movable along X, Y and Z axes. Although the welding nozzle cannot be rotated about the X and Z axes, the welding nozzle can be rotated about the Y axis. Other devices for applying coverings to workpieces are disclosed in U.S. Patent No. 3,769,486 and 3,865,525.

The concept of applying a plasma spray coating of from 30 to 40 thousandths of an inch in thickness to a workpiece, that is, a turbine vane, is disclosed in U.S. Patent No. 4,028,787. The well known process of rebuilding turbine vanes by manually applying a plasma spray covering can, at best, obtain a surface finish accuracy of plus or minus six mils (0.006 inch). The plasma spray build-up must be abraded in order to provide the desired surface measurements.

The application of thermal barrier coverings to airfoils has been attempted on an experimental basis using manually manipulated plasma spray guns. These experiments with the manual application of a plasma spray covering to an airfoil have been less than successful. This is due to the fact that it is a very slow process and the thickness of the plasma spray coating can, at best, be applied with an accuracy of plus or minus 6 mils (0.006 inch). In order to be acceptable for use in a turbine engine, a coating should be applied to the airfoil with an accuracy of at least plus or minus 1.5 mils (0.0015 inch).

The concept of applying coverings to airfoils are also disclosed in U.S. Patent No. 3,068,556 and 1,755,321. These patents contemplate that the coverings will be more or less uniform in thickness. The concept of using plasma spray techniques to deposit a wear resisting covering of a non-uniform thickness to a workpiece is disclosed in U.S. Patent No. 4,003,115. In addition, the concept of using

- 3 -

electroslag welding procedures to apply metal from a plurality of electrodes in layers of different thicknesses to a workpiece is disclosed in U.S. Patent No. 3,778,580.

5 The aforementioned prior art patents disclosing different methods of applying coverings to workpieces do not disclose how the thickness of the covering is to be measured. However, there are many known devices for measuring distances. Thus, U.S. Patent No. 3,940,608
10 discloses an optical sensing apparatus which is utilized to determine the displacement of an object from a given position. This patent contemplates that the distance will be measured by measuring the intensity of the light reflected from the object and determining the location of
15 that intensity on a curve which compares the intensity of the reflected light to the distance from the object.

 The concept of measuring changes in the location of an object by detecting changes in the location of the focal point of a lens is disclosed in U.S. Patent No.
20 3,016,464. However, this patent does not disclose the concept of using such a sensing apparatus in association with an apparatus which is utilized to control the application of a covering to a workpiece.

25 Brief Summary of the Present Invention

 The present invention provides a new and improved method and apparatus for applying a covering of either uniform or non-uniform thickness to a workpiece. When a
30 non-uniform covering is applied to a workpiece, the resultant product will have a configuration which is different than the configuration of the workpiece to which the covering was applied. The workpiece to which the covering is applied can have many different constructions and may be
35 formed of many different materials so long as the workpiece

- 4 -

is capable of receiving the covering.

In one specific utilization of the invention, a covering of a uniform thickness is accurately applied to an airfoil. In another specific utilization of the invention, an airfoil is formed on a workpiece or core which is subsequently removed from the airfoil. It should be understood that it is contemplated that the present invention could be utilized in association with many different types of objects other than airfoils.

10 An apparatus constructed in accordance with the present invention includes a spray gun which is utilized to direct a flow of one or more materials toward a workpiece, such as an airfoil. A sensor assembly is provided to determine the thickness of the covering applied to the workpiece. A control assembly is connected with the sensor assembly and the spray gun. The control assembly is effective to compare the thickness of the covering of material which is actually applied to the workpiece with a desired thickness and is effective to regulate the operation of the spray gun in such a manner as to effect the application to the workpiece of a covering having the desired thickness. Since adaptive controls are utilized, none of the articles are rejected.

25 Although it is contemplated that many different types of sensor assemblies could be utilized in association with the plasma spray gun to determine the thickness of the covering applied to the workpiece, an optical sensor assembly is advantageously utilized. The optical sensor assembly is utilized to detect when a surface area on either the workpiece or a covering is at the focal point of a lens. This is accomplished by sensing changes in the light reflected from the surface area with changes in the distance between the sensor assembly and the workpiece.

35 -- During changes in the distance between the work-

- 5 -

piece and the sensor assembly in one direction, the light reflected from the workpiece back to a photosensor decreases as the distance between the sensor assembly and the surface area approaches a focal length distance. As this is occurring, the light reflected back to a light source increases. Once the focal length distance is reached between the surface area and the sensor assembly, a minimum amount of light is reflected back to the photosensor and a maximum amount of light is reflected back to the light source. Continued relative movement between the sensor assembly and the workpiece results in an increase in the amount of light reflected to the photosensor and a resulting decrease in the amount of light reflected back to the light source. Therefore, it is possible to detect when the surface area and sensor assembly are spaced apart by the focal distance by detecting when the amount of light reflected to the photosensor stops decreasing and starts increasing.

By utilizing the method and apparatus of the present invention, it is possible to control the operation of a plasma spray gun to apply a covering which will have a thickness which is within 1.5 mils (0.0015 inch) of a desired thickness. The accurate application of the covering to the workpiece is promoted by detecting the thickness of the covering at several different points on the workpiece and controlling the operation of the plasma spray gun as a function of differences between the desired covering thickness and the actual covering thickness as sensed at several points on the workpiece. A printer assembly provides a permanent record of the actual thickness of the covering at various points on the workpiece.

The application of a covering of the desired thickness to the workpiece is further promoted by applying the covering in layers formed of longitudinally extending strips. The central axes of the strips in one layer are

- 6 -

offset from the central axes of the strips of a next adjacent layer.

When the covering is to be applied to a workpiece having a complex configuration, such as an airfoil, the accurate application of the covering is greatly promoted by utilizing an apparatus having six degrees of freedom of relative movement. Thus, an apparatus constructed in accordance with the present invention can effect relative movement between the airfoil and a spray gun along three different axes. In addition the apparatus can effect rotational movement between the airfoil and the spray gun about three axes. The speed of relative movement between the airfoil and spray gun can be varied to vary the thickness of the covering applied in each strip of material applied to the airfoil.

The airfoil is provided with a plurality of coverings. In one specific instance, a bond covering is applied to the airfoil and a thermal barrier covering is applied over the bond covering. A transition covering formed of a mixture of the bond and thermal covering materials is advantageously utilized between the bond and thermal barrier coverings to promote a strong inter-connection between the bond and thermal barrier coverings.

Accordingly, one of the features of the present invention is to provide a new and improved method and apparatus for effecting the accurate application of a covering, which may have either a uniform or non-uniform thickness, to a workpiece which can be formed of any material capable of receiving the covering.

Another feature of this invention is to provide a new and improved method and apparatus for applying a covering of material to at least a portion of a workpiece which may be an airfoil and wherein a sensor is utilized to detect the thickness of the covering of material applied to the workpiece and a control assembly regulates.

- 7 -

the operation of a spray gun as a function of the difference between the detected thickness of the covering and the desired thickness of the covering.

Another aspect of this invention is to provide
5 a new and improved apparatus for applying a covering to at least a portion of a workpiece, such as an airfoil, with a spray gun and wherein relative movement can occur between the workpiece and spray gun along each of three transversely extending axes and wherein relative rotation
10 can occur between the workpiece and spray gun about each of three axes.

Another feature of this invention is to provide a method and apparatus to measure the thickness of a covering applied to a workpiece without engaging the
15 covering with a solid object.

Another aspect of this invention is to provide a new and improved method of determining the location of a surface by detecting when the amount of light reflected back to a light source stops increasing and starts decreasing during relative movement between a lens and the
20 surface.

Another feature of this invention is to provide a new and improved airfoil having a sprayed covering with a thickness which varies by an amount which is less than
25 0.003 of an inch.

Another feature of this invention is to provide a new and improved method of making an airfoil and wherein material is sprayed on to a base having a configuration which is different than the configuration of the
30 airfoil to form a non-uniform covering having an exterior surface with a configuration which corresponds to the configuration of the airfoil.

Another feature of this invention is to provide a new and improved method and apparatus for accurately
35 applying a covering to a workpiece, such as an airfoil,

and wherein the workpiece is held by a single gripper assembly during both the application of the covering to the workpiece and during measurement of the thickness of the covering.

5

Brief Description of the Drawings

The foregoing and other objects and features of the present invention will become more apparent upon a
10 consideration of the following description taken in connection with the accompanying drawings wherein:

Figure 1 is a schematic illustration of an apparatus which is constructed in accordance with the present invention and is utilized to apply a covering to
15 at least a portion of a workpiece, which in Figure 1 is an airfoil;

Figure 2 is an enlarged illustration of the airfoil with a portion of a covering which was applied with the apparatus of Figure 1, broken away;

20 Figure 3 is a pictorial illustration of the apparatus of Figure 1;

Figure 4 is an enlarged illustration of a portion of the apparatus of Figure 3 and illustrating the relationship between the airfoil, a plasma spray gun for applying
25 a coating of material to the airfoil, and a sensor assembly which is utilized to detect the thickness of a covering applied to the airfoil;

Figure 5 is a schematic illustration depicting the manner in which relative movement occurs between the
30 airfoil and the plasma spray gun of Figure 4;

Figure 6 is an enlarged pictorial illustration depicting the construction of a drive apparatus which effects relative movement between the airfoil and the plasma spray gun in the manner shown schematically in
35 Figure 5;

- 9 -

Figure 7 (on sheet four of the drawings) is a schematic illustration of the manner in which cooling fluid flows through internal passages in an airfoil as the plasma spray gun applies heated material to the air-
5 foil;

Figure 8 is a schematic illustration depicting the construction of the sensor assembly of Figure 4;

Figure 9 is a graph depicting how the output from a photosensor of the sensor assembly of Figure 8
10 varies with variations in the distance between the sensor assembly and a surface area from which light is reflected;

Figure 10 is an enlarged graphic illustration of a portion of the curve of Figure 9 and illustrating the relationship between the curve and readings which are
15 taken to detect when the sensor assembly and a surface area from which light is reflected are spaced apart by a distance equal to the focal length of a lens;

Figure 11 is a schematic illustration of control apparatus used to control the operation of the plasma
20 spray gun and sensor assembly of Figure 4 and the drive apparatus of Figure 6;

Figure 12 is a pictorial illustration of a core or workpiece which is utilized as a base in the making of an airfoil;

25 Figure 13 is a sectional view through the core after a plurality of layers of material have been applied to the core with the apparatus of Figures 1 and 3 to at least partially form the airfoil;

Figure 14 is a sectional view, generally similar
30 to Figure 13, illustrating the relationship between a protective coating applied over the layers of Figure 13 and the core;

Figure 15 is a sectional view, generally similar to Figure 14, illustrating the airfoil with the core
35 removed; and

- 10 -

Figure 16 is a sectional view, generally similar to Figure 15, schematically illustrating the manner in which pressure is applied against the airfoil to increase its density.

5

Description of Specific Preferred
Embodiments of the Invention

General Description of the Apparatus

10 An apparatus 20 for use in applying a covering having a uniform or non-uniform thickness to a workpiece 22 is illustrated in Figures 1 and 3. The apparatus 20 includes a spray gun 24 which is used to apply the covering to the workpiece 22. A sensor assembly 28 is utilized
15 to determine the thickness of the covering applied to the workpiece 22 by the spray gun 24. A control apparatus 32 is utilized to control the operation of the spray gun 24 to apply a covering of a desired thickness to the workpiece 22.

20 The control apparatus 32 co-operates with the sensor assembly 28 and spray gun 24 to effect an extremely accurate application of material on the workpiece 22. Although the accuracy with which the material has to be applied to the workpiece will vary with variations in the
25 workpiece and the environment in which it is to be used, in one specific instance the thickness of the covering varied by less than plus or minus 1.5 mils (0.0015 inch) from a desired thickness. In order to accurately determine the thickness of the covering, the sensor assembly
30 28 is capable of repeatedly detecting the thickness of the covering with an error of less than 0.5 mils (0.0005 inch).

 In order to obtain the accurate application of a covering to a workpiece having a complex configuration,
35 a drive apparatus 36 is utilized to effect relative move-

- 11 -

ment between the workpiece 22 and the spray gun 24 along each of three orthogonal axes which have been indicated as the X, Y and Z axes in Figure 1. In addition, the drive apparatus 36 is effective to rotate the workpiece about each of the three axes in the manner indicated schematically by the arcuate arrows 40, 42, and 44 in Figure 1. By providing six degrees of freedom of relative movement between the workpiece and the spray gun 24, that is relative movement can occur between the spray gun 24 and workpiece 22 along each of three axes and relative rotational movement can occur around each of three axes, a workpiece 22 having a complex configuration can be accurately sprayed with a covering of material by the gun 24.

Although it is contemplated that the workpiece 22 could be moved along each of the three axes and rotated about each of the three axes, in the illustrated embodiment of the invention, the drive apparatus 36 is effective to move the workpiece along the X and Y axes and to move the spray gun 24 along the Z axis. Accordingly, the drive apparatus 36 includes a workpiece drive assembly 48 (Figure 1) which is operable by the control apparatus 32 to move the workpiece 22 relative to the spray gun 24 along the X and/or Y axes and to rotate the workpiece around the X, Y, and/or Z axes.

A spray gun drive assembly 50 is provided to move the spray gun 24 along the Z axis. It should be noted that the Z axis has been considered as extending through the centre of the workpiece and that the spray gun 24 is displaced to one side of the Z axis. Although the spray gun 24 is displaced at one side of the Z axis, it is moved along the Z axis by the drive apparatus 50 in the manner illustrated schematically by the arrow 54 in Figure 1. It should be understood that although in the illustrated embodiment of the invention it is preferred

- 12 -

to effect rotational movement of the workpiece 22 relative to the spray gun 24 about the X, Y, and Z axes, the spray gun 24 could be rotated relative to the workpiece 22 in such a manner as to effect one or more of the rotational components of relative movement between the spray gun 24 and workpiece 22. In addition, the spray gun 24 could be moved along the X and Y axes if desired.

In addition to the workpiece drive assembly 48 and the spray gun drive assembly 50, a sensor drive assembly 58 is provided to effect relative movement between the sensor assembly 28 and the workpiece 22. In the present instance, the sensor assembly 28 is moved along only the Z axis by the drive assembly 58 in the manner indicated schematically by the arrow 60 in Figure 1. However, the workpiece drive assembly 48 is operable to effect movement of the workpiece 22 relative to the sensor assembly 28 along the X and Y axes and to rotate the workpiece 22 about the X, Y, and Z axes. Thus, six degrees of freedom of relative movement are available between the workpiece 22 and the spray gun 24 and between the workpiece and the sensor assembly 28.

It is contemplated that the workpiece 22 could have many different constructions and could be formed of many different materials. The primary requisite for the workpiece 22 is only that it be able to receive and support a covering applied to it by the spray gun 24. In the present instance, the workpiece 22 is an airfoil (see Figure 2) which is utilized in a turbine engine.

The spray gun 24 is of the electric arc plasma spray type which is capable of directing heat-softened particles entrained in a high velocity plasma stream toward the airfoil 22. The plasma spray gun 24 (Figure 3) is of the multiport type which is supplied with powdered material of two different compositions. The plasma spray

- 13 -

gun 24 is a 40kw unit made by Plasmadyne, Inc., a division of Geotel, Inc. of Amityville, New York, U.S.A. and is of the same general type as the plasma spray guns illustrated in U.S. Patent Nos. 3,914,573 and 2,961,335. Although a specific spray gun has been disclosed herein, it should be understood that the present invention contemplates that many different types of spray guns could be utilized if desired and that the invention is not to be limited to having the spray gun 24 to be of any particular type unless so required by the appended claims.

A covering 64 (Figure 2) is applied to a blade portion 68 of the airfoil 22. Thus the covering extends over the major side surfaces 66, longitudinally extending leading and trailing edges 70 and 72, the top surface of a platform at a root end portion 74, and a tip end portion 76 of the airfoil 22. If the trailing edge of the blade 68 is provided with cooling passages, the trailing edge is not covered to prevent blockage of the passages. The general construction of the airfoil 22 is well known and will not be further described herein in order to provide prolixity of description.

The covering 64 which is applied to the airfoil 22 by the spray gun 24 includes a bond coat or covering 80 which is applied directly against the surface of the airfoil 22. The bond covering 80 is also effective to prevent oxidation of the airfoil 22. A thermal barrier coating or covering 82 is applied over the bond covering 80. It is contemplated that a transition covering formed by a mixture of the materials used in the thermal barrier and bond coverings could be utilized between the two coverings to provide a strong interconnection capable of withstanding severe operating conditions.

Although it is contemplated that the covering 64 could have many different compositions, in one specific instance the bond covering 80 was a NiCrAlY covering

- 14 -

which was 4 mils (0.004 inch) thick. The bond covering 80 was applied by moving the gun 24 at a uniform surface scan speed of approximately 16 inches per second. The bond covering 80 was applied in a plurality of passes of the spray gun 24 with a covering of approximately 2 mils (0.002 inch) thickness being applied on a first pass of the gun 24 and 1 mil (0.001 inch) being applied on each subsequent pass of the spray gun 24.

The thermal barrier covering 82 was formed of yttria stabilized zirconium oxide. The thermal barrier covering can be approximately 12 to 30 mils thick depending upon the requirements for the particular airfoil. The thermal barrier zirconium oxide covering 82 was applied in a number of passes of the gun 24. A covering of approximately 0.8 mils thickness was applied on each successive pass of the gun. However, it should be understood that the thickness of the covering applied on each pass of the gun 24 can be varied by varying the speed of movement of the gun relative to the airfoil or by varying the feed rate of material to the gun.

Although only a bond covering 80 and thermal barrier covering 82 have been shown in Figure 2, a transition covering is advantageously applied to the bond covering before the thermal barrier covering is applied. This transition covering is formed of a mixture of the materials in the bond and thermal barrier coverings. The transition covering promotes a strong connection between the bond and thermal barrier coverings even though they have different coefficients of thermal expansion. In the specific embodiment described above, the transition covering is formed by a mixture of yttria stabilized zirconia and NiCrAlY alloy.

The bond and thermal barrier coverings 80 and 82 each have a thickness which varies by less than 1.5 mils (0.0015 inch) from a desired thickness throughout

- 15 -

the area of the coating overlying the blade 68. If a transition covering is utilized, it is applied with a similar degree of accuracy.

5 This high degree of accuracy in the application of the coating 64 to the airfoil 22 is necessitated by the fact that the airfoil is utilized in a turbine engine. During operation of the engine, the airfoil 22 is rotated at an extremely high speed so that any error in the coating 64 would result in relatively high centrifugal stresses
10 being set up in the airfoil 22. In addition, it is necessary to have an accurately formed outer surface for the coating 64 due to the fact that high temperature gases flow past the outer surface of the coating at extremely high velocities. Of course, if a covering was
15 being applied to a different type of workpiece, a lesser degree of accuracy might be acceptable.

It should be understood that although particular covering thicknesses, compositions and modes of application have been set forth herein to facilitate understanding of the invention, it is contemplated that other
20 covering thicknesses and compositions could be utilized. It should also be understood that the invention is not, except when required by the appended claims, to be limited to a multilayered covering for an airfoil or to a covering having a particular degree of accuracy in regard to
25 the thickness of the covering. This is because although the apparatus 20 is extremely well suited and can advantageously be utilized to provide thermal barrier coverings for airfoils, it is contemplated that the
30 apparatus will be utilized to provide many different types of coverings on many different types of articles.

Method of Applying a Covering to an Airfoil

Although it is contemplated that the apparatus 20 will be utilized to apply coverings to many different
35 articles, the method of applying the covering 64 to the

- 16 -

airfoil 22 will be described to illustrate one specific method of operating the apparatus 20. Of course, the apparatus 20 could be constructed differently and operated in a different manner if the characteristics of the article being covered so require or allow.

When the multilayer covering 64 is to be applied to the airfoil 22 by the apparatus 20, the airfoil is mounted in a gripper assembly 86 (see Figures 3 and 4). The gripper assembly 86 engages the root or platform end 88 (see Figure 2) of the airfoil 22 and is provided with a shield or barrier plate 92 (Figure 4). The barrier plate 92 prevents excess spray from the gun 24 impinging directly against the clamp which holds the root end portion 88 of the airfoil. The barrier plate 92 also shields the root and edges of the platform. This tends to minimize thermal effects on the clamp and resulting inaccuracies in the positioning of the airfoil 22. In addition, a stream of a cooling fluid, in the present instance carbon dioxide gas, is directed against the airfoil 22 to cool the airfoil and further reduce thermal effects.

The directing of a stream of cooling fluid against the airfoil 22 is effective to minimize thermal effects. However, when an airfoil having an internal passage is being sprayed, further cooling can be obtained by directing a flow of fluid through the passage in the airfoil. The manner in which this could be accomplished is illustrated schematically in Figure 7. Thus, a flow of cooling fluid from a source 93 is conducted through a conduit 94 to a longitudinally extending internal passage 95 in the airfoil 22. The central passage 95 is connected with openings in the trailing edge of the airfoil by passages 97. It should be emphasized that the apparatus 20 operates satisfactorily to apply coverings to airfoils without utilizing additional coolant flow through internal

- 17 -

passages in the airfoil. However, when the airfoil is constructed with internal passages, providing a flow of cooling fluid through these passages does serve to further alleviate thermal effects.

5 Once the airfoil has been mounted in the gripper assembly 86, the exact locations of a plurality of points on the outer surface of the airfoil 22 are determined by using the sensor assembly 28. The exact locations of the various points on the surface of the airfoil 22 are
10 transmitted to the control assembly 32 (Figures 1 and 3) where they are stored for future reference. It should be noted that since the sensor assembly 28 is immediately adjacent to the spray gun 24, the position of various portions of the surface of the airfoil 22 can be
15 accurately determined by the sensor assembly 28 while the airfoil 22 is held by the same gripper assembly 86 (Figure 4) as is used to hold the airfoil during the application of the covering 64 to the airfoil by the spray gun 24.

 Once the exact location of various points on the
20 surface of the airfoil 22 have been determined, the control apparatus 32 (Figure 1) effects movement of the workpiece drive assembly 48 to accurately position the airfoil 22 in front of the spray gun 24. The spray gun 24 is then activated. Powdered material for the bond
25 covering 80 (Figure 2) is entrained in a suitable gas and conducted in a known manner to the spray gun through a hose or conduit 96 (see Figure 4). At this time electrical energy and cooling liquids are conducted to and from the spray gun 24 through hoses or conduits 98 and 100. In
30 addition, inert gas such as argon is connected to the spray gun 24 through the hose or conduit 102.

 The spray gun 24 is activated and an electric arc is produced. Gas fed under pressure through the conduit 102 is conducted through the arc. The gas is ionized and
35 heated in the electric arc. The heated ionized gas is a

- 18 -

body of plasma which flows toward a spray gun exit port 106. Powdered material from the conduit 96 is directed into the high-temperature accelerating stream of plasma where it is heated. The heated powder particles are entrained in the plasma stream and are directed by the spray gun 24 against the airfoil 22. When the bond covering 80 is being applied, the powdered material conducted through the conduit 96 and directed toward the workpiece is an NiCrAlY alloy.

As the plasma stream leaves the spray gun 24 and is directed toward the airfoil 22, a spray gun drive motor 110 (Figure 4) is operated to drive a vertical screw 112 which extends parallel to the Z axis. This moves the spray gun upward at a uniform speed so that the plasma stream is effective to apply a generally vertically extending strip of material to the airfoil 22.

Assuming that the rate of flow of heated material from the gun 24 remains constant, the thickness of the covering applied over a surface area of the blade can be controlled by controlling the speed of movement of the gun. Thus, when a relatively thick strip is to be applied to the airfoil, the control assembly 32 effects operation of the drive motor 110 to move the spray gun at a relatively slow speed. When a relatively thin covering is to be applied, the control assembly 32 causes the motor 110 to operate at a higher speed.

When the spray gun 24 reaches the end of a vertical upward stroke, it directs the plasma stream above the airfoil 22. The control apparatus 32 is then effective to activate the workpiece drive assembly 48 to index the airfoil 22. This causes a next adjacent portion of the airfoil 22 to be aligned to receive material from the spray gun 24. The spray gun 24 is then moved downwardly to apply a next succeeding strip of material to the airfoil 22 adjacent to and overlapping the preceding

- 19 -

strip. In one specific instance, the strips were approximately 12 mm wide and had central axes which were spaced 5 mm apart.

When the spray gun 24 reaches the end of a vertical downward stroke, it directs the plasma stream beneath the airfoil 22. The airfoil 22 is then indexed again to position it to receive the next succeeding strip. This next strip is adjacent to and overlaps the last strip. The next strip is applied to the airfoil 22 as the spray gun 24 is moved upwardly along the Z axis by operation of the motor 110 under the influence of the control apparatus 32.

The strips of material are applied in succession around the airfoil 22 by moving the spray gun 24 along the Z axis and by accurately positioning the airfoil relative to the spray gun before each stroke is undertaken. It should be noted that although the airfoil 22 has an extremely complex configuration, successive surface areas on the airfoil can be accurately positioned relative to the spray gun 24 by the drive assembly 48. This is because the drive assembly 48 can move the airfoil along the X and Y axes and can rotate the airfoil about the X, Y, and Z axes. The exact positions to which the airfoil is indexed on each of the work strokes of the spray gun 24 is determined by a program in the control assembly 32.

After the first layer of the bond coat covering 80 has been applied to the airfoil 22, the spray gun 24 is operated to apply a next succeeding layer over the first layer. The longitudinally extending strips of the next succeeding layer have central axes which may be offset from the central axes of the strips of the first layer. This is done because there tends to be a slightly greater accumulation of material at the centre of the strip than at the edges of the strip. By offsetting the longitudinal axes of the strips of adjacent layers of

- 20 -

material, variations in the thickness of the bond coating 80 are minimized. It should be noted that the control apparatus 32 can effect operation of the drive assembly 48 to cause a slight dithering or sidewise movement of the blade along the X axis during a vertical stroke of the spray gun 24 along the Z axis to thereby promote blending of the strips applied to the airfoil 22 during work strokes of the spray gun 24.

The accuracy with which the covering is applied to the airfoil is promoted by applying the covering in successive layers with the longitudinal axes of the strips in each layer offset relative to the longitudinal axes of the strips of the next adjacent layer. However, sufficient uniformity of covering thickness (plus or minus 1.5 mils) may be obtained without offsetting the longitudinal central axes of the strips. In addition, the total thickness of a covering can be applied by spraying a plurality of strips on top of each other and then indexing the blade and spraying a plurality of strips adjacent to the first group of strips. It is contemplated that the specific manner in which the strips are applied will be varied to suit the configuration of a particular workpiece to which they are being applied and the accuracy with which the covering must be applied to the workpiece.

When the spray gun 24 has been operated to apply a number of layers of bond covering 80 to the airfoil 22, the thickness of the bond covering 80 is measured. In accomplishing this, the airfoil 22 is moved along the X axis from a spray receiving position adjacent to the spray gun 24 to a position adjacent to the sensor assembly 28. The sensor assembly 28 is then operated to detect the thickness of the bond covering 80 which has been applied to the airfoil.

It is contemplated that when the first measure-

- 21 -

ment is made the bond covering 80 may have a thickness which is less than the desired thickness at each of the locations where the sensor assembly 28 initially sensed the position of the airfoil surface. The control assembly 32 determines the difference between the desired thickness and the actual thickness of the bond covering 80 applied to the airfoil 22 by the operation of the spray gun 24. This thickness determination is made while the airfoil remains in the gripper assembly 86. If the airfoil 22 was removed from the gripper assembly 86, errors would, in all probability, be introduced when the airfoil was repositioned in the gripper assembly.

Once the control apparatus 32 has determined the extent to which the actual thickness of the initial portion of the covering 80 differs from the desired thickness of the bond covering, the airfoil 22 is moved back into alignment with the spray gun 24. The spray gun 24 is then operated in the manner previously explained to increase the thickness of the bond covering as and where required.

After the spray gun 24 has been operated to increase the thickness of the initial covering 80 by an amount which the control apparatus 32 determines is sufficient to result in the covering having a desired thickness, the sensor assembly 28 is again utilized to detect whether or not the actual thickness of the bond covering 80 is the desired thickness. If the control apparatus 32 determines that additional material should be applied to the covering 80 in order that it will have the requisite thickness, the airfoil 22 is again moved into alignment with the spray gun 24 and additional material is applied to the airfoil. When the covering 80 is completed, it has a thickness which differs from the desired thickness by less than plus or minus 1.5 mil (0.0015 inch). It should be noted that, due to the thin-

- 22 -

ness of the bond coat, it is often possible to achieve the required thickness of plus or minus 1.5 mils in the first spray sequence.

After the bond covering 80 has been applied in the manner previously explained, a thermal barrier covering 82 is applied directly over the bond covering without removing the airfoil 22 from the gripper assembly 86. In the present instance, the thermal barrier covering 82 is formed of yttria stabilized zirconia. The thermal barrier covering has a thickness of between 12 and 30 mils depending upon the environment in which the airfoil 22 is to be utilized.

The spray gun 24 is used to apply the thermal barrier covering 82 to the airfoil 22 in the same manner in which the spray gun was used to apply the bond covering 80 to the airfoil. However, during the application of the thermal barrier covering 82, powdered yttria stabilized zirconia is conducted to the multiport spray gun 24 through the conduit 120 (see Figure 4).

The spray gun 24 is then effective to direct a plasma spray of yttria-stabilized zirconia toward the airfoil 22 in the manner previously explained in connection with the bond covering 80. As the spray of yttria stabilized zirconia is directed toward the airfoil 22, the spray gun drive motor 110 is operated to cause the drive screw 112 to move the spray gun 24 along a vertical path. During rotation of the drive screw 112, movement of the spray gun 24 along a path extending parallel to the Z axis is guided by a pair of upstanding rods 124 and 126 (Figure 4).

As the spray gun 24 is moved along the Z axis relative to the airfoil 22, strips of yttria stabilized zirconia are sequentially applied to the airfoil 22. These strips extend from the root end portion 74 of the airfoil to the tip end portion 76 of the airfoil. In order to obtain a thermal barrier covering 82 of a desired thickness,

- 23 -

a plurality of layers of strips of material are sequentially applied to the airfoil 22. Any tendency to form longitudinally extending relatively thick areas in the thermal barrier covering 82 is minimized by offsetting the longitudinal axes of strips in adjacent layers of the thermal barrier covering or by judicious selection of strip overlaps.

When the thermal barrier covering 82 has been built up to a thickness which is somewhat less than the desired thickness, the workpiece drive assembly 48 (see Figure 1) is operated to move the airfoil 22 (see Figure 4) to a position adjacent to the sensor assembly 28. The sensor assembly 28 is utilized in conjunction with the control apparatus 32 (Figure 1) to detect the actual thickness of the thermal barrier covering 82. It should be noted that the airfoil 22 remains in the gripper assembly 86 from the time that the location of various points on the airfoil are sensed by the sensor assembly 28 prior to initiation of the application of the bond covering 80 until the thermal barrier covering 82 is completed. This eliminates any possibility of errors which could result from connecting and disconnecting the airfoil 22 from the gripper assembly 86.

Once the control apparatus 32 has determined the amount by which the thickness of the thermal barrier covering 82 must be increased in order to provide a coating of a desired thickness, the spray gun 24 is again operated to increase the thickness of the thermal barrier coating 82. The sensor assembly 28 is operated to sense the thickness of the thermal barrier coating at a plurality of locations on the airfoil 22. If for some unforeseen reason the thermal barrier covering 82 should have different thicknesses at different locations on the airfoil 22, the control apparatus 32 is effective to cause the spray gun 24 to operate in such a manner as to

- 24 -

eliminate the variations in the thickness of the thermal barrier covering 82.

Accordingly, if it was detected that the initial operation of the spray gun 24 caused the application of a relatively thick initial thermal barrier covering 82 to a portion of the airfoil and a somewhat thinner thermal barrier covering to another portion of the airfoil, the control apparatus 32 would effect operation of the spray gun to make a plurality of passes or scans along the airfoil in the area where the thermal barrier coating 82 is relatively thin and would make a fewer number of passes or scans along the portion of the airfoil 22 where the thermal barrier coating was relatively thick. The thickness of the covering applied in a portion of a strip can be varied by varying the speed of movement of the spray gun 24 as a strip is applied. By repetitively sensing the thickness of the thermal barrier covering 82 and controlling the operation of the spray gun 24 with the control apparatus 32 as a function of the sensed thickness of the thermal barrier covering at a plurality of locations on the airfoil 22, the thermal barrier covering 82 will have a thickness which varies by less than 3 mils (0.003 inch).

Although the thermal barrier covering 82 is applied directly over the bond covering 80 on the airfoil 22, it is contemplated that a transition covering may be utilized between the bond and thermal barrier coverings. When a transition covering is to be provided, the control assembly 32 is effective to cause the spray gun 24 to apply a mixture of the bond covering materials and the thermal barrier covering materials over the bond covering 80 before the thermal barrier covering 82 is applied. The thickness of the transition covering is measured with the sensor assembly 28 in the manner previously explained in connection with the bond and thermal

- 25 -

barrier coverings.

When a transition covering of the desired thickness has been applied to the airfoil, the thermal barrier covering is applied over the transition covering.

5 It should be noted that the airfoil 22 is continuously maintained in the gripper assembly 86 during application of the bond covering, measuring of the thickness of the bond covering, application of the transition covering, measuring of the thickness of the transition covering,
10 application of the thermal barrier covering and measuring of the thickness of the thermal barrier covering.

Although the operation of the spray gun 24 has been described herein in connection with the application of a bond covering 80 and a thermal barrier covering 82
15 to an airfoil 22, it is contemplated that the method and apparatus of the present invention will be utilized to apply coverings over portions of many different types of workpieces. It is contemplated that the coverings applied to these workpieces will be formed of many different types
20 of materials and that there may or may not be a plurality of coverings applied to the same workpiece by the spray gun. In addition, it is contemplated that spray guns other than the particular plasma spray gun disclosed herein will be utilized to apply different types of
25 materials to the workpieces.

Workpiece Drive Assembly

The workpiece drive assembly 48 is illustrated schematically in Figure 5. A specific embodiment of the workpiece drive assembly 48 is shown in Figure 6.

30 The workpiece drive assembly 48 includes a carriage 130 which is supported for movement along both the X and Y axes (Figure 5). Although they could have different orientations, the Y axis extends generally parallel to the path of flow of material from the spray gun 24.
35 The X axis extends generally perpendicular to the path of

flow of material from the spray gun 24.

Accordingly, the carriage 130 is supported for movement along the X axis by a pair of parallel guide bars 134 and 136 (see Figure 5). The guide bars 134 and 136 are fixedly connected to a pair of parallel longitudinally extending upper frame members 138 and 140 (Figure 3) of a framework 142.

The carriage 130 is supported for movement along the Y axis by a pair of parallel support rods 146 and 148 (see Figure 6). The support rods 146 and 148 are connected with the guide bars 134 and 136 by four bearing blocks, only two of which are shown at 150 and 152 in Figure 5. The carriage 130 is connected with the support bars 146 and 148 by suitable bearings 154 and 156 and 158 (Figure 6).

Thus, the carriage 130 is supported for movement along the X axis by the parallel guide bars 134 and 136. The carriage 130 is supported for movement along the Y axis by the parallel guide bars 146 and 148. Of course, the guide bars 146 and 148 move along the X axis with the carriage 130.

In order to effect movement of the carriage 130 along the X axis and the guide bars 134 and 136, a drive screw 162 is rotated by a reversible electric motor 164. It should be noted that the drive screw 162 extends parallel to the X axis and the guide bars 134 and 136. The drive screw 162 is connected with the bearing block 150 by a suitable ball nut or internally threaded drive element.

Similarly, the carriage 130 is moved along the Y axis and the parallel guide bars 146 and 148 by a drive screw 166. The drive screw 166 is rotated by a reversible drive motor 168 (Figure 5).

In order to enable the airfoil 22 to be rotated about the mutually perpendicular X, Y, and Z axes, the

- 27 -

airfoil engaging gripper assembly 86 is connected with a lower end portion of a longitudinally extending support member 172 (Figure 5). The support member is pivotally connected with the carriage 130 at a universal joint 176.

- 5 The universal joint 176 connects the support member 172 with the carriage 130 so as to allow the gripper assembly 86 freedom of sidewise movement in every direction within certain defined limits.

10 Accordingly, the universal joint 176 allows the support member 172 to rotate about its own longitudinally extending central axis to provide for rotational movement of the gripper assembly 86 and workpiece about the Z axis. The pivot joint 176 also enables the support member 172 to be pivoted about a point which is coincident with the centre of the universal joint in the manner
15 that the support member 172 moves in a conically shaped envelope and the gripper assembly 86 moves through a circle relative to the carriage 130. This enables the airfoil 22 to be pivoted about both the X axis and the Y
20 axis.

To effect pivotal movement of the airfoil 22 about the X axis, a slide member 180 (see Figures 5 and 6) is movable under the influence of a reversible drive motor 182 (Figure 6) and a drive screw 184. Upon operation
25 of the drive motor 182, the drive screw 184 effects movement of the slide member 180 along a path which extends parallel to the Y axis. This movement of the slide member 180 is effective to pivot the support member 172 about the X axis at the universal joint 176.

30 The support member 172 is pivoted about the Y axis by movement of a second slide member 188 under the influence of a reversible electric drive motor 190 (see Figure 6) and a drive screw 192. Upon operation of the reversible drive motor 190, the drive screw 192 moves
35 the slide 188 along a path which extends parallel to the

X axis and perpendicular to the Y axis. This effects pivotal movement of the support member 172 about the Y axis at the universal joint 176.

5 In order to effect rotational movement of the airfoil 22 about the Z axis which is perpendicular to the X and Y axes, a drive motor 196 is operable through a speed reduction assembly 198 to rotate the support member 172 about its central axis. It should be understood that although operation of the motor 182 effects pivotal movement of the workpiece about the X axis and that operation of the motor 190 effects pivotal movement of the workpiece about the Y axis, both motors could be simultaneously operated to effect simultaneous pivotal movement of the airfoil 22 about the pivot joint 176 to any desired position relative to the spray gun 24 and sensor assembly 28. 10 Simultaneously therewith the motor 196 could be energized to rotate the airfoil 22 about the Z axis. It is also contemplated that simultaneously with pivotal movement of the airfoil 22 about the X, Y, and Z axes, the drive 15 motors 164 and 168 could be energized to move the airfoil 22 along the X and Y axes.

It is believed that it will be apparent that the workpiece drive assembly 48 provides for five degrees of freedom of relative movement of the workpiece 22 relative to the spray gun 24 and sensor assembly 28. Thus, the 25 workpiece 22 can be moved along the X and Y axes and can be pivoted about the X, Y, and Z axes by the drive assembly 48. The sixth degree of freedom of relative movement between the workpiece and the spray gun 24 and 30 sensor assembly 28 is achieved by the spray gun drive assembly 50 and the sensor drive assembly 58.

The spray gun drive assembly 50 includes the motor 110 (Figure 4) which rotates the drive screw 112 through a pair of gears 199 and 200. Upon operation of the reversible electric drive motor 110, the spray gun 24 is moved 35

- 29 -

along the vertical guide bars 124 and 126 which extend parallel to the Z axis.

The sensor assembly 28 is moved by the drive assembly 58 in much the same manner as in which the spray gun 24 is moved by the drive assembly 50. Thus, the drive assembly 58 includes a reversible electric motor 205 (Figure 4) which is connected by a pair of gears 206 and 207 with a vertical drive screw 208. The drive screw 208 extends parallel to the Z axis and to a pair of upright guide members 209 and 211. Thus, upon operation of the reversible electric drive motor 205 the sensor assembly 28 is moved along the Z axis by the drive screw 208.

Although a specific workpiece drive assembly 48, spray gun drive assembly 50, and sensor drive assembly 58 has been described herein, it is contemplated that drive assemblies having different constructions could be utilized to obtain relative movement between a workpiece and the spray gun 24 and sensor assembly 28 along the X, Y and Z axes and to obtain relative rotational movement therebetween about the X, Y, and Z axes. For example, it is contemplated that the spray gun 24 and sensor assembly 28 could be stationary. The workpiece drive assembly 48 would then be effective to move the workpiece along all three axes and to rotate the workpiece about all three axes. Similarly, the workpiece could be stationary and the spray gun 24 and sensor assembly 58 could be moved along all three axes and rotated about all three axes. However, the combination of the workpiece drive assembly 48, spray gun drive assembly 50 and sensor drive assembly 58 is believed to be a particularly advantageous way to obtain the desired movement between the workpiece, spray gun and sensor assembly.

Sensor Assembly

The sensor assembly 28 is utilized in determining the thickness of the covering applied to a workpiece, such

as the airfoil 22. The sensor assembly 28 utilizes electrical energy to detect the thickness of a covering without engaging the covering with a solid object.

The sensor assembly 28 includes an electric
5 light 210 which is a noncoherent light source (Figure 8). Light from the lamp 210 is directed into a fibre optic bundle 214. The light from the fibre optic bundle 214 is transmitted through a lens assembly or optical extender 216 against a surface 218 of the airfoil 22. At least a
10 portion of the light is reflected back from the surface 218 of the airfoil 22 to a fibre optic bundle 224 which leads to a photosensor 226.

The two fibre optic bundles 214 and 224 (Figure 8) are randomly mixed in a main fibre optic bundle 228.
15 Therefore, a portion of the light which is reflected from the surface 218 is directed back to the light source 210 through the fibre optic bundle 214 while the remainder of the light is directed to the photosensor 226 through the fibre optic bundle 224.

20 The lens assembly 216 includes a collimating lens 232 and a condensing lens 234. The condensing lens 234 is effective to direct the light from the light source toward a focal point which has been indicated at 236 in Figure 8. The construction of the sensor assembly 28 is
25 the same as is disclosed in U.S. Patent No. 3,940,608 and is commercially available from MTI Instruments, Latham, New York as a model KD-100 Fotonic Sensor and has a 2.2 millimetre diameter probe.

The sensor assembly 28 provides a clear indica-
30 tion of when a surface area on an object is spaced apart from the condensing lens 234 by a distance which is equal to the focal length of the lens. When the surface area of the airfoil 22 is at the focal point, as shown in Figure 8, the amount of light which is reflected back to
35 the light source 210 is maximized and the amount of light

- 31 -

which is reflected to the sensor tends to be minimized. This is because the light rays reflected from the surface of the workpiece 22 through the condensing lens 234 and collimating lens 232 are directed back to the same fibre optic conduits from which they originated, that is back to the fibre optic conduits in the bundle 228 leading to the bundle 214. The manner in which this occurs has been shown graphically in Figure 9.

When the probe is against the workpiece, that is when the probe to target distance is zero mils, none of the light is reflected back to the photosensor 226 (Figure 9). As the distance from the collimating lens 234 and the surface area of the airfoil 22 increases, the light reflected back to the photosensor 226 increases in a reasonably linear manner until a distance approaching to the focal distance is approached. The light reflected back to the photosensor 226 then begins to decrease.

For a lens assembly having the characteristics indicated by the graph in Figure 9, the light reflected back to the photosensor begins to decrease when the lens 234 is spaced approximately 420 mils from the surface 218 of the airfoil 22. This sharp decrease continues until the focal point distance is reached at approximately 433 mils. As the distance increases from the focal point distance, the amount of light reflected from the photosensor 226 sharply increases again until the lens 234 is located about 460 mils from the surface of the workpiece. The light reflected back to the photosensor then decreases in a reasonably linear manner as the distance increases.

It should be understood that the relationship between the amount of light reflected to the light source 210 from the surface 218 varies in a manner which is substantially inverse to the manner in which the light reflected to the photosensor 226 varies with movement of the sensor assembly 28. Thus, when the sensor assembly 28

- 32 -

is spaced from the surface 218 by a distance equal to the focal distance of the lens 234, the amount of light reflected to the photosensor 226 tends to be minimized. At this time, the amount of light reflected to the light source 210 is maximized. As the distance between the lens 234 and the surface 218 changes to either side of the focal point distance, that is becomes either greater or lesser than 433 mils, the amount of light reflected to the light source 210 decreases as the amount of light reflected to the photosensor 226 increases in the manner shown in Figure 9.

In effecting measurement of the covering applied to the airfoil 22, the uncoated airfoil is moved by the workpiece drive assembly 48 relative to the sensor assembly 28 until the surface of the airfoil is at the focal point, that is until the surface of the workpiece is spaced apart from the lens 234 by the focal distance of 433 mils. The position of the airfoil 22 at this time is stored in the control apparatus 32. This original positioning of the airfoil 22 provides a reference position from which subsequent measurements are determined.

When a substantial portion of a covering, such as the bond coat covering 80, has been applied to the airfoil 22 in the manner previously explained, the thickness of this initial covering is measured without engaging the covering. To this end, the workpiece drive assembly 48 is operated under the influence of the control assembly 32 to position the outer surface area of the initial portion of the covering at the focal point of the lens 234. When the surface area of the covering is at the focal point of the lens 234, that is when the surface area of the covering is 433 mils from the lens 234, the position of the airfoil 22 will be offset from its original or reference position by a distance equal to the thickness of the covering.

- 33 -

The control apparatus 32 can determine the actual thickness of the initial portion of the covering applied to the airfoil 22 by subtracting the position of the airfoil when the outer surface area of the covering is at the focal point of the lens 23⁴ from the previously stored reference position. The thickness of the initial portion of the covering is then compared with the desired thickness of the covering to determine the amount by which the thickness of the initial portion of the covering would be increased in order to have a covering of the desired thickness. The control apparatus 32 then effects operation of the spray gun 24 to increase the thickness of the covering until it has the desired thickness. In this manner, the thickness of the bond coat covering 80 can be controlled to within plus or minus 1.5 mils (0.0015 inch) of a desired thickness.

Once the bond coat covering 80 has been applied to the airfoil, the thermal barrier coat covering 82 is applied over the bond coat covering. In determining the thickness of the thermal barrier covering 82, the initial reference position of the airfoil is utilized. The combined thickness of the bond coat covering 80 and the portion of the thermal barrier coat covering 82 which has been applied to the airfoil 22 is measured. This combined thickness is compared with a desired combined thickness for both coverings to determine the amount by which the thickness of the thermal barrier covering 82 must be increased. The thickness of the thermal barrier covering can also be controlled to within plus or minus 1.5 mils (0.0015 inch).

The manner in which the focal point for the lens 23⁴ is detected has been illustrated graphically in Figure 10. A set of ten memory locations is set up in the control apparatus 32 to constitute a first-in-first-out (FIFO) memory. After the airfoil 22 has been moved

- 34 -

slightly closer to the sensor assembly 28 than the focal distance, the airfoil is moved away from the sensor assembly 28 in 0.0002 inch increments.

On the first step the voltage is read and entered into the first memory location in the first-in-first-out memory. On each successive step of the workpiece relative to the sensor, a new voltage reading is entered into the first memory location and all previous measurements are moved back by one memory location. A reading which has reached the last memory location is lost on the next step. Therefore, the memory always contains the last ten voltage readings and their corresponding probe coordinate steps.

When the first reading exceeds the last by a specified voltage, the value representing the focal point is assumed to have been detected and the coordinate of the sixth memory location is taken as the valley position. The program in the control apparatus 32 is set up to detect the negative slope preceding the valley and the positive slope following the valley by looking for appropriate differences between the first and last reading to the FIFO memory. Parameters that can be varied automatically if searching for the valley are the voltage differences to define the slopes and the valley and the position in which the valley detect routine starts. The manner in which the readings in the FIFO memory relate to a curve of photosensor output voltage has been illustrated schematically in Figure 10. If it is assumed that the sensor assembly 28 is being moved away from the workpiece 22, that is toward the left as viewed in Figure 8, the initial data entered into the FIFO memory could be considered as being relative to the photosensor output voltage curve in the manner illustrated schematically at 242 in Figure 10. It should be noted that at the position indicated at 242 in Figure 10 the tenth reading, that is

- 35 -

the reading being taken, is substantially less than the zero reading, that is the reading stored in the tenth memory location of the FIFO memory. After the sensor assembly 28 has been moved away from the workpiece through the focal point, the readings stored in the FIFO memory locations could be considered as being relative to the photosensor output voltage curve in the manner illustrated schematically at 240 in Figure 10. Thus at this time the tenth reading, that is the reading being taken, is substantially larger than the zero reading, that is the reading stored in the tenth memory location of the FIFO memory. Therefore, it can be readily determined that in moving the sensor assembly 28 from the position indicated at 242 in Figure 10 to the position indicated at 240 in Figure 10 the bottom of the valley or focal point position was passed.

In proceeding from the position illustrated schematically at 242 in Figure 10 to the position illustrated at 240 in Figure 10 the tenth reading, that is the reading being taken, will be less than the first or zero reading until the position indicated schematically at 244 is reached. In moving from the position illustrated at 242 to the position illustrated schematically at 244, the sensor assembly moves through the position in which the focal point of the lens 234 is on the surface of the workpiece. It should be noted that after the sensor assembly 28 moves through the focal point position, the successive voltage readings, that is the tenth reading being taken, will stop decreasing and start increasing.

When the sensor assembly 28 has moved through the focal point position to the position indicated schematically at 244 in Figure 10, the voltage reading being taken, that is the tenth reading, will be approximately equal to but slightly less than the voltage reading

- 36 -

stored in the tenth memory location. On the next successive incremental step of relative movement between the sensor assembly and the workpiece, the voltage reading being taken, that is the tenth reading, will exceed the voltage reading stored in the tenth memory location. This indicates that the bottom of the valley or focal point is disposed at a location between the location where the tenth voltage reading is being taken and the location where the zero voltage reading was previously taken. Since the readings will have shifted slightly to the right of the centre of the bottom of the valley, the reading stored in the sixth FIFO memory location is assumed to have been made at the focal point position. Of course, the readings in each of the FIFO memory locations could be compared in order to determine which reading was the lowest to more accurately determine the focal point position.

It should be understood that in the illustrated embodiment of the invention the relative movement between the sensor assembly 28 and the workpiece 22 is obtained by moving the workpiece relative to the sensor assembly with the drive apparatus 36. However, the sensor assembly could be moved relative to the workpiece in the manner assumed above in connection with Figure 10. It should be understood that although the sensor assembly 28 has been described herein in connection with a method of applying a covering to a workpiece, it is contemplated that the sensor assembly could be used in association with a FIFO memory to locate any surface. For example, the sensor assembly could be utilized in association with an operation in which material is removed from a workpiece.

Another feature of the program is that the number of measurements taken in each step can be one or any multiple of two up to one hundred and twenty-eight. The value entered into the FIFO memory is then the average of

- 37 -

the readings minimizing random noise effects. The number of memory locations in the FIFO can be varied up to any desired number. This process of detecting the focal point of the lens 234 shows a measurement repeatability with an error of less than plus or minus 0.5 mils (0.0005 inch).

In the embodiment of the invention described herein the airfoil or workpiece 22 has been moved relative to the sensor assembly 28 to detect when a surface on the workpiece is spaced a predetermined distance, that is the focal distance, from the sensor assembly. It is contemplated that the sensor assembly could be moved relative to the workpiece or airfoil 22 if desired. Although for safety reasons it is preferred to approach the focal distance from a point which is closer to the workpiece than the focal distance, that is by increasing the distance between the sensor assembly 28 and the workpiece or airfoil 22, it is contemplated that the focal point could be detected by decreasing the distance between the workpiece or airfoil 22 and the sensor assembly 28.

It is also contemplated that other types of sensor assemblies could be utilized if desired. For example, a sensor assembly using a coherent light source (laser gauge), or a capacitive sensor could be utilized if desired. It is believed that the accuracy with which measurements are made will be promoted with any known type of sensor by maintaining the workpiece or airfoil 22 in the clamp assembly 86 during both the application of a covering to the airfoil and measurement of the covering.

Control Apparatus

It is contemplated that many different types of known control systems could be utilized to control the operation of the workpiece drive assembly 48, the spray gun drive assembly 50, and the sensor drive assembly 58 to determine when the desired coating thickness has been obtained. However, in the illustrated embodiment of the

- 38 -

invention, the control apparatus includes a microprocessor 250 (see Figure 11) having peripheral interface adaptors 252, 254, 256, and 258 connected with the various drive motors, the optical sensor assembly, display outputs and manual control inputs, and the spray gun 24. Although the control circuitry connected with the X axis drive motor 164 has been shown in Figure 11, it should be understood that similar control circuitry is connected with the spray gun and sensor drive motors 110 and 205 and with the other drive motors in the workpiece drive assembly 48, that is with the drive motors 168, 182, 190, and 196. Although the microprocessor 250 could have many different constructions, in one specific instance the microprocessor 250 was a type M 6800 microprocessor from Motorola Communications & Electronics, Inc. of Phoenix, Arizona.

In order to simplify the control circuitry, zero reference stops are utilized with all of the various drive motors, including the X axis drive motor 164. Provision of zero reference stops allowed position encoders to be eliminated. Accordingly, a reference register was provided for each motor in association with a digital comparator and an up/down counter.

For the purpose of making measurements, the optical sensor 28 was connected with an analog-to-digital convertor which was sampled by the microprocessor control system. The memory locations which constituted the first-in-first-out memory unit were also provided in the microprocessor.

In accordance with a feature of the present invention, a printer 262 (see Figure 11) is provided in the control apparatus 32 to provide a printed record of the thickness of the covering applied to the airfoil. Thus, the sensor assembly 28 is utilized to detect the thickness of the covering applied to the airfoil 22 at a plurality of points on the airfoil. The printer 262 is.

- 39 -

utilized to record the thickness of the bond coat covering 80 and the thermal barrier coat covering 82 at each of a plurality of points on the airfoil 22. If a transition covering is utilized between the bond and thermal barrier coverings, the printer 262 would also record the thickness of the transition covering at each of a plurality of points on the airfoil.

In accordance with another feature of the invention, the control assembly 32 is effective to compensate for any variations which may occur during the application of the various coverings to the airfoil 22. This is because the sensor assembly 28 is utilized during the operation of the apparatus 20 to detect any deviations which may occur in the thickness of the covering. The control assembly 32 is effective to regulate operation of the spray gun 24 to compensate for any deviation in the thickness of the covering. During normal operation of the apparatus 20 this results in zero defects.

Method of Making an Airfoil

In the foregoing description, the apparatus 20 has been described in connection with the application of bond covering 80 and a thermal barrier covering 82 of uniform thicknesses to an airfoil. However, it is contemplated that the apparatus 20 will be utilized to apply non-uniform coverings with the resulting construction of a three dimensional object having a configuration which has very little resemblance to the configuration of the work-piece upon which the non-uniform covering is deposited. In Figures 12 to 16 an example of an application of such a non-uniform covering to fabricate an airfoil is disclosed. However, it should be emphasized that a non-uniform covering could be applied to any base capable of receiving the covering in order to provide for the build-up of material in such a manner as to form an object having any desired configuration.

- 40 -

In fabricating an airfoil in accordance with the method illustrated in Figures 12 to 16, a core 270 is provided. Although the core 270 does have a configuration which slightly resembles the configuration of an airfoil, it is contemplated that the core 270 could have any desired configuration. In the present instance the configuration of the core 270 was selected in order to provide internal passages of a desired configuration within the airfoil.

The core 270 is covered with a plurality of non-uniform layers, which have been indicated at 274 in Figure 13, to form the basic configuration of an airfoil. It should be noted that the layers 274 were applied with the spray gun 24 by making more scans or passes across areas where the material is relatively thick than across areas where the material is relatively thin. Reference locations corresponding to the location of many different points on the surface of the core 270 were stored in the microprocessor before the non-uniform covering 274 was applied.

By detecting the shifts in the position of the core when the outer surface areas of the non-uniform covering 274 overlying the various reference points were at the focal point of the lens 234 (Figure 8), it is possible to determine the thickness of the non-uniform coating 274 at many different points. By controlling the operation of the spray gun 24 in the manner previously explained, it is possible to accurately build up a non-uniform coating over the core 270. The thickness of the non-uniform coating will vary by less than plus or minus 1.5 mils (0.0015 inch).

Once the body of the airfoil has been built up by the non-uniform covering 274, a thermal barrier covering 278 is applied over the non-uniform covering 274.

The thermal barrier covering 278 is of a material which is

- 41 -

different than the material of the covering 274 and may be provided with a bond coat or covering, similar to the bond covering 80 of Figure 2.

Once the thermal barrier covering 278 has been applied to the non-uniform covering 274, the core or base 270 is removed to provide an internal passage 282 in the airfoil 284 (see Figure 15). The hollow airfoil 284 is then subjected to hot isostatic pressing to increase the density of the airfoil 284 and to eliminate any porosity which may be present in the non-uniform coating 274.

The core 270 can be made of any material which does not adversely react with the non-uniform covering 274 and which is easily removed as by being melted out or leached. With one particular type of airfoil, the core 270 could advantageously be made of aluminium.

Summary

In view of the foregoing description, it is apparent that the present invention provides a new and improved method and apparatus for applying a covering of either uniform or non-uniform thickness to a workpiece. When a non-uniform covering is applied to a workpiece, the resultant product will have a configuration which is different than the configuration of the workpiece to which the covering was applied. The workpiece to which the covering is applied can have many different constructions and may be formed of many different materials so long as the workpiece is capable of receiving the covering.

In one specific utilization of the invention, a covering 64 of a uniform thickness is accurately applied to an airfoil 22. In another specific utilization of the invention, an airfoil 284 is formed on a workpiece or core 270 which is subsequently removed from the airfoil. It should be understood that it is contemplated that the present-invention could be utilized in association with

- 42 -

many different types of objects other than airfoils.

An apparatus constructed in accordance with the present invention includes a spray gun 24 which is utilized to direct a flow of material toward a work-
5 piece, such as the airfoil 22. A sensor assembly 28 is provided to determine the thickness of the covering 64 applied to the workpiece 22 without engaging the work-
10 piece. A control assembly 32 is connected with the sensor assembly 28 and the spray gun 24. The control assembly 32 is effective to compare the thickness of the covering of material which is actually applied to the workpiece 22 with a desired thickness and is effective to regulate the operation of the spray gun 24 in
15 such a manner as to effect the application to the workpiece of a covering having the desired thickness.

Although it is contemplated that many different types of sensor assemblies 28 could be utilized in association with the plasma spray gun 24 to determine the thickness of the covering applied to the workpiece,
20 an optical sensor assembly is advantageously utilized. The optical sensor assembly 28 is utilized to detect when a surface area on either the workpiece or a covering is at the focal point of a lens 234. This is accomplished by sensing changes in the light reflected from the surface
25 area with changes in the distance between the sensor assembly 28 and the workpiece.

During changes in the distance between the workpiece and the sensor assembly in one direction, the light reflected from the workpiece 22 back to a photosensor 226
30 decreases as the distance between the sensor assembly and the surface area approaches a focal length distance (Figure 9). As this is occurring, the light reflected back to a light source 210 increases. Once the focal length distance is reached between the surface area and
35 the sensor assembly 28, a minimum amount of light is

- 43 -

reflected back to the photosensor 226 (Figure 2) and a maximum amount of light is reflected back to the light source 210. Continued relative movement between the sensor assembly 28 and the workpiece 22 results in an increase in the amount of light reflected to the photosensor 226 and a resulting decrease in the amount of light reflected back to the light source 210. Therefore, it is possible to detect when the surface area and sensor assembly are spaced apart by the focal distance by detecting when the amount of light reflected to the photosensor 226 stops decreasing and starts increasing.

By utilizing the method and apparatus of the present invention, it is possible to control the operation of the plasma spray gun 24 to apply a covering 64 which will have a thickness which is within 1.5 mils (0.0015 inch) of a desired thickness. The accurate application of the covering 64 to the workpiece 22 is promoted by detecting the thickness of the covering at several different points on the workpiece and controlling the operation of the plasma spray gun 24 as a function of differences between the desired covering thickness and the actual covering thickness as sensed at several points on the workpiece.

The application of a covering 64 of the desired thickness to the workpiece 22 is further promoted by applying the covering in layers formed of longitudinally extending strips. The central axes of the strips in one layer may be offset from the central axes of the strip of a next adjacent layer for more precise control of overall thickness uniformity.

When the covering is to be applied to a workpiece having a complex configuration, such as the airfoil 22, the accurate application of the covering is greatly promoted by utilizing a drive apparatus 36 having six

- 44 -

degrees of freedom of relative movement. Thus, an apparatus constructed in accordance with the present invention can effect relative movement between the airfoil and a spray gun along three different axes. In addition
5 the apparatus can effect rotational movement between the airfoil and the spray gun about three axes, that is, the X, Y, and Z axes.

- 1 -

Claims:

1. Apparatus for applying a covering of material to at least a portion of a workpiece, said apparatus comprising spray means for directing a flow of material toward the workpiece, sensor means for detecting the thickness of a covering of material applied to the workpiece by said spray means, and control means connected with said sensor means and said spray means for comparing the detected thickness of the covering of material with a desired thickness and for regulating the operation of said spray means as a function of the difference between the detected thickness of the covering and the desired thickness of the covering.

2. An apparatus as set forth in claim 1 wherein said control means includes means for effecting relative movement between said spray means and the workpiece in such a manner as to effect the application to the workpiece of a covering having different thicknesses over different surface areas of the workpiece.

3. An apparatus as set forth in claim 1 further including first means for effecting relative movement between said spray means and the workpiece along each of

- 2 -

three transversely extending axes and second means for effecting rotational movement between said spray means and the workpiece about each of three transversely extending axes.

4. An apparatus as set forth in claim 1 wherein said control means includes means for effecting operation of said sensor means to detect the thickness of the covering in each of a plurality of predetermined locations on the workpiece, said control means including means for comparing the detected thickness of the covering at each of the plurality of locations with the desired thickness of the covering at each of the locations and for regulating the operation of said spray means as a function of the difference between the detected thickness of the covering at each of the plurality of locations and the desired thickness of the covering at each of the plurality of locations.

5. An apparatus as set forth in claim 1 further including drive means for effecting relative movement between said sensor means and the workpiece to vary the distance therebetween, said sensor means including a light source, lens means for directing light from said light source against a surface area in such a manner as to cause the amount of light reflected from the surface area back to the light source to increase as the distance between said sensor means and the surface changes in a first direction from a first distance to a predetermined distance during operation of said drive means to change the distance between said sensor means and the workpiece and to cause the amount of light reflected from the surface area back to the light source to decrease as the distance between said sensor means and the surface area changes in the first direction from the predetermined distance to a second distance, said control means including means for detecting when the amount of light reflected

- 3 -

back to the light source stops increasing and starts decreasing to thereby detect when said sensor means is spaced apart from the surface area by the predetermined distance.

6. An apparatus as set forth in claim 5 wherein said control means includes means for effecting operation of said sensor means to direct light from said light source against a plurality of surface areas disposed in predetermined locations relative to the workpiece, said control means being effective to detect when the amount of light reflected back to the light source from each of the plurality of surface areas stops increasing and starts decreasing.

7. An apparatus as set forth in claim 1 further including drive means for moving said spray means relative to the workpiece along a first path during the application of the covering of material to the workpiece and for moving said sensor means relative to the workpiece along a second path which extends parallel to the first path during detection of the thickness of the covering of material applied to the workpiece.

8. An apparatus as set forth in claim 1 further including means for supplying to said spray means powdered material having a first composition, means for supplying to said spray means powdered material having a second composition, said control means including means for effecting operation of said spray means to apply a first covering of the first composition over the workpiece, for effecting operation of said spray means to apply a transition covering which is a mixture of the first and second compositions over the first covering, and for effecting operation of said spray means to apply a second.

- 4 -

covering of the second composition over the transition covering.

9. . An apparatus for use in accurately applying a covering of material to at least a portion of an airfoil, said apparatus comprising spray means for applying material to the airfoil, means for supplying material in a powdered form to said spray means, said spray means including means for heating the material and directing a flow of the heated material toward the airfoil, drive means for effecting relative movement between the airfoil and said spray means to enable the flow of heated material to be distributed over the surface of the airfoil to form a covering, sensor means for detecting the thickness of the covering applied to the airfoil to within less than 0.0005 inch of the actual thickness of the covering, and control means connected with said spray means, drive means and sensor means for effecting operation of said spray means to apply to the airfoil a covering having a thickness which differs from a desired thickness by less than 0.0015 inch.

10. A method of applying a covering of a desired thickness to at least a portion of a workpiece, said method comprising the steps of applying to the workpiece an initial covering having a thickness which is less than the desired thickness by operating a spray means to direct a flow of material toward the workpiece, determining the thickness of the initial covering, comparing the thickness of the initial covering with the desired covering thickness to determine the difference between thickness of the initial covering and the desired covering thickness, and increasing the thickness of the covering to the desired thickness by operating the spray means to direct a flow of material toward the initial covering.

11. A method as set forth in claim 10 further including the steps of effecting relative movement between the spray means and the workpiece along each of three transversely extending axes and effecting rotational movement between the spray means and the workpiece about each of three transversely extending axes to thereby vary the spatial relationship between the spray means and the workpiece.

12. A method as set forth in claim 10 wherein said step of determining the thickness of the initial covering includes the steps of providing a source of light, directing light from the light source against a surface area of the initial covering with a lens, reflecting light from the surface area to a photosensor, decreasing the amount of light reflected back to the photosensor by effecting relative movement between the lens and the surface area of the initial covering in one direction, subsequently increasing the amount of light reflected back to the photosensor by continuing to effect relative movement between the lens and the surface area of the initial covering in the one direction and detecting when the lens is spaced apart from the surface area of the initial covering by a predetermined distance by detecting when the amount of light reflected back to the photosensor stops decreasing and starts increasing as the distance between the lens and the surface area of the initial covering is changed in the one direction.

13. A method as set forth in claim 10 wherein said step of applying an initial covering to the workpiece includes the steps of applying a plurality of layers of material to the workpiece to form the initial covering, said steps of applying a plurality of layers of material to the workpiece including the steps of applying one of

- 6 -

the layers in strips and applying the next succeeding layer in strips having longitudinal axes which are offset from longitudinal axes of the strips of the one layer.

14. A method as set forth in claim 10 wherein said step of operating a spray means includes the steps of supplying material in a powdered form to said spray means, heating the material, and directing a flow of the heated material toward the workpiece.

15. A method as set forth in claim 14 wherein the workpiece has an internal passage and the method further includes the step of inducing a flow of fluid through the internal passage while directing the flow of heated material toward the workpiece.

16. A method as set forth in claim 10 wherein said step of determining the thickness of the initial covering includes the step of utilizing electrical energy from a source of electrical energy to detect the thickness of the initial covering without engaging the initial covering.

17. A method of applying a covering of material over at least a portion of an airfoil, said method comprising the steps of providing an airfoil and operating a spray means to apply to the airfoil a covering having a thickness which differs from a desired thickness by less than 0.0015 inch, said step of operating a spray means includes the steps of supplying material in powdered form to the spray means, heating the material, and directing a flow of the heated material toward the airfoil.

18. A method as set forth in claim 17 further including the steps of effecting relative movement between the spray means and the airfoil along each of three transversely extending axes and effecting rotational movement between the spray means and the airfoil about

- 7 -

each of three transversely extending axes to thereby vary the spatial relationship between the spray means and the airfoil.

19. A method of determining the location of a surface, said method comprising the steps of providing a source of light, directing light from the light source against the surface with a lens, reflecting light from the surface back to the light source, increasing the amount of light reflected back to the light source by varying the distance between the lens and the surface in a first direction, subsequently decreasing the amount of light reflected back to the light source by continuing varying the distance between the lens and the surface in the first direction, and detecting when the lens is spaced apart from the surface by a predetermined distance by detecting when the amount of light reflected back to the light source stops increasing and starts decreasing.

20. An airfoil comprising a root end portion, a tip end portion, a pair of edge portions extending between said tip and root end portions, a pair of major side portions extending between said edge portions, at least one of said portions having a sprayed covering thereon, said covering including a plurality of layers formed of strips which were sequentially sprayed on at least the one portion of the airfoil, said covering as sprayed having a thickness which varies by an amount which is less than 0.003 of an inch.

21. A method of applying a covering over at least a portion of a workpiece, said method comprising the steps of holding the workpiece with a gripper means, providing a spray means which is selectively operable to direct a flow of material having either a first composition or a second

- 8 -

composition toward the workpiece while it is held by said gripper means, operating the spray means to direct a flow of material having the first composition toward the workpiece to form over at least a portion of the workpiece an initial covering having a thickness which is less than a first predetermined thickness and is formed of material having the first composition while the workpiece is held by said gripper means, detecting the thickness of the initial covering while holding the workpiece with said gripper means, operating the spray means to increase the thickness of the initial covering of material having the first composition to the first predetermined thickness while holding the workpiece with the gripper means, operating the spray means to direct a flow of material having the second composition toward the workpiece to form over at least a portion of the initial covering a second covering having a thickness which is less than a second predetermined thickness and is formed of material having the second composition while the workpiece is held by the gripper means, detecting the thickness of the second covering while holding the workpiece with the gripper means, and operating the spray means to increase the thickness of the second covering of material having the second composition to the second predetermined thickness while holding the workpiece with the gripper means.

22. An apparatus for use in applying a covering of material to at least a portion of a workpiece, said apparatus comprising gripper means for holding the workpiece, spray means for directing a flow of material toward the workpiece while it is held by said gripper means, drive means for effecting relative movement between said spray means and said gripper means, sensor means for

detecting the location of a point on the surface of a covering of material applied to the workpiece by said spray means while the workpiece is held by said gripper means, and control means connected with said spray means, drive means, and sensor means for effecting operation of said spray means to apply to the workpiece a covering having a point on its outer surface which is disposed in a predetermined location relative to the workpiece.

23. An apparatus comprising a source of light, lens means for directing light from the source of light against a surface and for directing light reflected from the surface back to said source of light, drive means for varying the distance between said lens means and the surface in a first direction to first increase the amount of light reflected back to said source of light and to subsequently decrease the amount of light reflected back to said source of light from the surface, and means for detecting when the amount of light reflected back to said light source stops increasing and starts decreasing as the distance between said lens means and the surface is varied in the first direction to detect when said lens means is spaced apart from the surface by a predetermined distance.

24. An apparatus as set forth in claim 23 wherein said means for detecting when the amount of light reflected back to said light source stops increasing and starts decreasing includes means for storing data corresponding to the amount of light reflected back to the light source at each of a plurality of distances between said lens means and the surface, means for comparing the stored data for a plurality of distances, and means for determining when the stored data indicates that

0007207

- 10 -

the light reflected back to said source of light stops increasing and starts decreasing.

1 / 8




FIG. 1





FIG. 2

FIG. 3






FIG. 4








FIG. 6



6 / 8



7 / 8




FIG. II




FIG. 12




FIG. 13




FIG. 14




FIG. 15




FIG. 16



European Patent
Office

EUROPEAN SEARCH REPORT

Application number

EP 79 30 1288

0007207

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
	<p>FR - A - 2 314 531 (NIPPON STEEL CORP.)</p> <p>* Page 4, lines 25-36; page 5, lines 27-38; pages 6-11; page 12, lines 1-28; figures 1-8 *</p> <p>--</p> <p>US - A - 3 711 312 (K. YOSHIDA)</p> <p>* Complete patent *</p> <p>--</p> <p>GB - A - 946 990 (F. HIRSCHMANN)</p> <p>* Complete patent *</p> <p>--</p> <p>US - A - 3 775 582 (W.F. ICELAND)</p> <p>* Complete patent *</p> <p>--</p> <p>DE - A - 2 748 490 (EUTECTIC CORP.)</p> <p>* Page 9, paragraph 2; page 10 - page 13; figures 1,2 *</p> <p>--</p> <p>DE - A - 2 743 833 (EUTECTIC CORP.)</p> <p>* Page 14, paragraph 2; page 15; page 16, paragraph 1; figure 1 *</p> <p>--</p> <p>D US - A - 3 940 608 (C.D. KIS-SINGER)</p> <p>* Complete patent *</p>	<p>1,2,4</p> <p>1</p> <p>1</p> <p>1</p> <p>3,14</p> <p>8,14,21</p> <p>19,23</p>	<p>B 05 B 13/04 12/00</p> <p>C 23 C 7/00</p> <p>F 01 D 5/28</p> <p>G 05 D 5/02</p> <p>G 01 D 5/30</p> <p>TECHNICAL FIELDS SEARCHED (Int. Cl. 3)</p> <p>B 05 B</p> <p>C 23 C</p> <p>F 01 D</p> <p>F 02 C</p> <p>B 23 K</p> <p>G 05 D</p> <p>G 01 D</p> <p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant</p> <p>A: technological background</p> <p>O: non-written disclosure</p> <p>P: intermediate document</p> <p>T: theory or principle underlying the invention</p> <p>E: conflicting application</p> <p>D: document cited in the application</p> <p>L: citation for other reasons</p> <p>&: member of the same patent family, corresponding document</p>
<p><input checked="" type="checkbox"/> The present search report has been drawn up for all claims</p>			
Place of search	Date of completion of the search	Examiner	
The Hague	19-10-1979	COLPAERT	

0007207



European Patent
Office

EUROPEAN SEARCH REPORT

Application number

EP 79 30 1286

-2-

DOCUMENTS CONSIDERED TO BE RELEVANT			CLASSIFICATION OF THE APPLICATION (Int. Cl. 3)
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	
D	<u>US - A - 3 016 464 (E.M. BAILEY)</u> * Column 4, lines 14-47; column 5, lines 18-25; figure 1 * --	19,23	
	<u>US - A - 3 792 928 (J.P. POILLEUX)</u> * Column 4, lines 52-67; columns 5-7; column 8, lines 1-42; figures 5-10 * --	19,23	
	<u>US - A - 3 758 233 (K.R. CROSS)</u> * Complete patent * ----	20	TECHNICAL FIELDS SEARCHED (Int. Cl. 3)